sarbak

TECHNICAL DATA SHEET

CW626N - CuZn33Pb1,5AlAs

S626

RODS / HOLLOW RODS

sarbak

CW626N - CuZn33Pb1,5AlAs

Product Code	EN Symbol	EN No	ASTM		Cu	Zn	Pb	Sn	Fe	As	Ni	Al	Mn	Others Total
S626	CuZn33Pb1,5AlA:	CW626N	-	Min (%)	64,0	Rem.	1,2	-	-	0,02	-	0,8	-	-
				Max (%)	66,0	Rem.	1,7	0,3	0,3	0,15	0,2	1	0,1	0,2

(*) Each of the other elements< 0,02 %

Features And Applications

CW626N is an alloy as a substitute for the alloy CW602N. CW626N meets ISO 6509 requirements regarding the dezincification resistance. Approximately 2 hours annealing at around 500 °C is recommended for EN ISO 6509 standard compliance after hot forging process. Depending on the process conditions, temperature and time can also change. Also this alloy compliance with UBA Hygienic list, 4MS, RoHS II and REACH directives.

4MS and UBA Hygienic list group for CW626N alloy: B, C, D

Area of Usage

Fitting parts used in aggressive (corrosive) water.

TECHNICAL SPECIFICATIONS

Structure	α	**Hot Forming**	700-800 °C
Machinability	% 70	**Soft Annealing**	500-550 °C
Density	8,4 g/cm³	**Soft Annealing Time**	2 hours
Electrical Conductivity	20 %IACS	**Stress Relieving**	200-250 °C
Thermal Conductivity	95 W/(m·K)	**Stress Relieving Time**	2 hours
Elasticity Module	96 kN/mm²	**Max. Depth of Dezincification**	<200 µm
Coeff. of Thermal Expansion	21,5 10^{6}/K		
Melting Point	875-900 °C		

Range of Products

S626 alloy can be produced in our extrusion and cold drawing unit as rods, hollows and profiles suitable for both forging and machining. Please contact us for other technical informations.

INDICATIVE SHAPED ENDS DIMENSIONS

Nominal Diameter or Width		Type A – Chamfer Lenght (L)		Type B – Point Lenght (L)	
Across-flats (mm)		**Min** (mm)	**Max** (mm)	**Min** (mm)	**Max** (mm)
Over	Up to and including				
-	10	0,2	1,5	2	7
10	20	0,2	2	3	10
20	30	0,2	3	4	12

Unless otherwise specified by the buyer, the shape of the ends of products larger than 30 mm is up to the supplier.





sarbak

CW626N - CuZn33Pb1,5AlAs

Nominal Diameter or Width Across-flats (mm)		Preferred (available) Lengths (mm)	Tolerance on Length (mm)
Over	Up to and including		
10 Inc.	30	3.000 - 4.000	±50
30	65	3.000 - 4.000	±100

Stress Relieving The polygonal rods and hollow rods are subjected to stress relieving treatment

Packaging 500 or 1000 kg bundle – 3/5 metal straps different bundle packagings, up to 10 mm dimension products are packed with wooden case

EN 12164 - Rods for Free Machining

Material Condition	Nominal Diameter (mm)		Width Across-flats (mm)		Tensile Strength Rm N/mm² (MPa)	0,2 % Proof Strength N/mm² (MPa)		Elongation			Hardness (HBW)	
	Over	Up to and inc.	Over	Up to and inc.	Min	Min	Max	A_{100mm} (%) Min	$A_{11,3}$ (%) Min	A (%) Min	Min	Max
M	All		All		As manufactured							
R280	10	65	10	55	280	-	200	-	25	30	-	-
H070	10	65	10	55	-	-	-	-	-	-	70	110
R320	10	60	10	50	320	200	-	-	15	20	-	-
H090	10	60	10	50	-	-	-	-	-	-	90	135
R400	10	15	10	13	400	250	-	-	5	8	-	-
H105	10	15	10	13	-	-	-	-	-	-	105	-

EN 12168 - Hollow Rods for Free Machining

Material Condition	Wall Thickness (mm)		Tensile Strength Rm N/mm² (MPa)	0,2 % Proof Strength N/mm² (MPa)		Elongation A (%)	Hardness (HBW)		Hardness (HV)	
	Over	Up to and inc.	Min	Min	Max	Min	Min	Max	Min	Max
M	All		As manufactured							
R280	4	All	280	-	200	30	-	-	-	-
H070	4	All	-	-	-	-	70	110	80	120
R320	4	20	320	200	-	20	-	-	-	-
H090	4	20	-	-	-	-	90	135	100	145
R400	4	8	400	250	-	8	-	-	-	-
H105	4	8	-	-	-	-	105	-	115	-

EN 12165 - Wrought and Unwrought Forging Stocks

Material Condition	Nominal Diameter (mm)		Hardness (HBW)	
	Over	Up to and including	Min	Max
M	All		As manufactured	
H070	10	65	70	110

sarbak

CW626N - CuZn33Pb1,5AlAs

STANDARD		EN 12164			EN 12165		EN 12168					
Dimension Range		Round Rod		Hexagonal, Square	Round Rod		Round and Hexagonal Hollow Rod, Outer Dim. Tol.			Hole Tolerance Round		Hole Tol. Hexagonal
Over	Up to & inc.	Class A	Class B	Rod	Class A	Class B	Class A	Class B	Class C	Class A	Class B	-
-	10	0 -0,06	0 -0,036	0 -0,09	±0,25	±0,14	-	-	-	-	-	-
10	13	0 -0,07	0 -0,043	0 -0,11	±0,25	±0,14	-	-	-	-	-	-
13	18	0 -0,07	0 -0,043	0 -0,11	±0,25	±0,14	-	-	-	±0,35	-	+0,70 -0
18	20	0 -0,08	0 -0,052	0 -0,13	±0,30	±0,17	-	-	-	±0,42	-	+0,84 -0
20	23	0 -0,08	0 -0,052	0 -0,13	±0,30	±0,17	-	-	-	±0,42	±0,17	+0,84 -0
23	26	0 -0,08	0 -0,052	0 -0,13	±0,30	±0,17	-	0 -0,21	-	±0,42	±0,17	+0,84 -0
26	30	0 -0,08	0 -0,052	0 -0,13	±0,30	±0,17	-	0 -0,21	0 -0,13	±0,42	±0,17	+0,84 -0
30	50	0 -0,16	-	0 -0,16	±0,60	±0,20	-	0 -0,25	0 -0,16	±0,80	±0,20	+1,6 -0
50	55	0 -0,19	-	0 -0,19	±0,70	±0,37	-	0 -0,46	0 -0,30	±0,95	±0,37	-
55	65	0 -0,19	-	-	±0,70	±0,37	±0,60	0 -0,46	0 -0,30	±0,95	-	-
65	80	-	-	-	±0,70	-	±0,60	0 -0,46	0 -0,30	±0,95	-	-
80	110	-	-	-	±2	-	-	-	-	-	-	-

For Hollow Rods
Minimum wall thickness is 4 mm. Eccentricity : % 8 (max.)
Minimum wall thickness is 5 mm over 65 mm
" For hollows, maximum outer diameter is 78 mm and maximum producible weight 28 kg in 1 meter."

Outer Cold Drawn - Internal Extruded
Outer Class B - Hole Class A tolerance

Inner-Outer Cold Drawn
Outer Class C - Hole Class B tolerance

Inner-Outer Extruded
Outer Class A - Hole Class A tolerance

Headquarter
Eğitim Mah. Adım Sok. Orjin İş Merkezi No: 10 -18 Kat: 3 Daire No: 39 - 49 34722
Hasanpaşa / Kadıköy / İstanbul / Turkey
T: +90 216 414 45 35 pbx | **F:** +90 216 414 45 40

Factory
Çerkezköy Organize Sanayi Bölgesi Gazi Osman Paşa Mah. 8.Cad. No: 3 59500
Çerkezköy / Tekirdağ / Turkey
T: +90 282 725 19 60 pbx | **F:** +90 282 725 19 70

www.sarbak.com.tr | www.ekosari.com