

sarbak



## TECHNICAL DATA SHEET

CW724R - CuZn21Si3P

ECOBASS

RODS / HOLLOW RODS



Product Code	EN Symbol	EN No	ASTM		Cu	Zn	Pb	Sn	Fe	Ni	Al	Mn	P	Si	Others Total
ECOBASS	CuZn21Si3P	CW724R	C69300	Min (%)	75,0	Rest	-	-	-	-	-	-	0,02	2,7	-
				Max (%)	77,0	Rest	0,09	0,3	0,3	0,2	0,05	0,05	0,10	3,5	0,2

(\*)Each of the other elements < 0,02 %

### Features And Applications

This lead free alloy is patented. Chips and parts should not be mixed with other alloys. It has many features such as good machinability, high durability, recyclability, perfect corrosion resistance, good forgeability. Ecobrass can be produced as rods, hollows, profiles suitable for both forging and machining. Ecobrass meets ISO 6509 requirements regarding the dezincification resistance. Also this alloy compliance with UBA Hygienic list, 4MS, ELV, RoHS II and REACH directives.

4MS and UBA Hygienic list group for CW724R alloy: B, C, D

### Area of Usage

Automotive industry, naval industry , plumbing and drinking water applications. Also this alloy suitable for drinking water application in USA and Canada Markets.

### Range of Products

CW724R can be produced in our extrusion and cold drawing unit as rods, hollows and profiles suitable for both forging and machining. Please contact us for other technical informations.


## TECHNICAL SPECIFICATIONS

Structure	kappa+gama	Melting Point	860-925 °C
Machinability	% 80	Hot Forming	680-750 °C
Density	8,25 g/cm <sup>3</sup>	Soft Annealing	530-650 °C
Electrical Conductivity	4,5 MS/m, 7,8 %IACS	Soft Annealing Time	1-3 Hours
Thermal Conductivity	35 W/(m·K)	Stress Relieving	200-300 °C
Elasticity Module	ca.100 GPa	Stress Relieving Time	1-3 Hours
Coeff. of Thermal Expansion	19.7 10 <sup>-6</sup> /K	Max. Depth of Dezincification	<100 µm

### INDICATIVE SHAPED ENDS DIMENSIONS

Nominal Diameter or Width		Type A - Chamfer Length (L)		Type B - Point Length (L)	
Across-Flats (mm)		Min (mm)	Max (mm)	Min (mm)	Max (mm)
Over	Up to and including				
-	10	0,2	1,5	2	7
10	20	0,2	2	3	10
20	30	0,2	3	4	12

Unless otherwise specified by the buyer, the shape of the ends of products larger than 30 mm is up to the supplier.





Nominal Diameter or Width Across-flats (mm)		Preferred (available) Lengths (mm)	Tolerance on Length (mm)
Over	Up to and including		
10 <sup>inc.</sup>	30	3.000-4.000	±50
30	65	3.000-4.000	±100

**Stress Relieving** The polygonal rods and hollow rods are subjected to stress relieving treatment  
**Packaging** 500 or 1000 kg bundle – 3/5 metal straps different bundle packagings, up to 10 mm dimension products are packed with wooden case

**EN 12164 - Rods for Free Machining**

Material Condition	Nominal Diameter (mm)		Width Across-Flats (mm)		Tensile Strength Rm N/mm <sup>2</sup> (MPa) Min	0,2 % Proof Strength N/mm <sup>2</sup> (MPa)		Elongation			Hardness (HBW)		
	Over	Up to and inc	Over	Up to and inc		Min	Max	A100mm (%)	A11,3 (%)	A (%)	Max	Max	
								Min	Min	Min			
M	All		All		As manufactured								
R500	10	65	10	55	500	-	450	-	-	15	-	-	
H130	10	65	10	55	-	-	-	-	-	-	130	180	
R600	10	25	10	20	600	300	-	-	-	12	-	-	
H150	10	25	10	20	-	-	-	-	-	-	150	220	

**EN 12168 - Hollow Rods for Free Machining**

Material Condition	Wall Thickness (mm)		Tensile Strength Rm N/mm <sup>2</sup> (MPa) Min	0,2 % Proof Strength N/mm <sup>2</sup> (MPa)		Elongation A (%) Min	Hardness (HBW)		Hardness (HV)		
	Over	Up to and inc		Min	Max		Min	Max	Min	Max	
											Min
M	All		As manufactured								
R500	4	20	500	-	450	15	-	-	-	-	
H130	4	20	-	-	-	-	130	180	140	190	
R600	4	20	600	350	-	12	-	-	-	-	
H150	4	20	-	-	-	-	150	220	160	230	

**EN 12165 - Wrought and Unwrought Forging Stocks**

Material Condition	Nominal Diameter (mm)		Hardness (HBW)	
	Over	Up to and inc	Min	Max
M	All		As manufactured	
H130	10	65	130	220

STANDARD		EN 12164			EN 12165		EN 12168				
Dimension Range		Round Rod		Hexagonal, Square	Round Rod		Round and Hexagonal Hollow Rod, Outer Dim. Tol.		Hole Tolerance Round		Hole Tol. Hexagonal
Over	Up to & inc.	Class A	Class B	Rod	Class A	Class B	Class A	Class B	Class A	Class B	-
-	10	0 -0,06	0 -0,036	0 -0,09	±0,25	±0,14	-	-	-	-	-
10	13	0 -0,07	0 -0,043	0 -0,11	±0,25	±0,14	-	-	-	-	-
13	18	0 -0,07	0 -0,043	0 -0,11	±0,25	±0,14	-	-	±0,35	-	+0,70 -0
18	20	0 -0,08	0 -0,052	0 -0,13	±0,30	±0,17	-	-	±0,42	-	+0,84 -0
20	23	0 -0,08	0 -0,052	0 -0,13	±0,30	±0,17	-	-	±0,42	-	+0,84 -0
23	26	0 -0,08	0 -0,052	0 -0,13	±0,30	±0,17	-	0 -0,21	±0,42	-	+0,84 -0
26	30	0 -0,08	0 -0,052	0 -0,13	±0,30	±0,17	-	0 -0,21	±0,42	-	+0,84 -0
30	50	0 -0,16	-	0 -0,16	±0,60	±0,20	-	0 -0,25	±0,80	-	+1,6 -0
50	55	0 -0,19	-	0 -0,19	±0,70	±0,37	-	0 -0,46	±0,95	-	-
55	65	0 -0,19	-	-	±0,70	±0,37	±0,60	0 -0,46	±0,95	-	-
65	80	0 -0,19	-	-	±0,70	±0,37	±0,60	0 -0,46	-	-	-
80	90	-	-	-	±2	-	-	-	-	-	-

### For Hollow Rods

Minimum wall thickness is 4 mm. Eccentricity: %8 (max).

Minimum wall thickness is 5 mm over 65 mm.


**"For hollows, maximum outer diameter is Ø78 mm and maximum producible weight is 28 kg in 1 meter."**

#### Outer Cold Drawn - Internal Extruded

Outer Class B - Hole Class A tolerance

#### Inner-Outer Extruded

Outer Class A - Hole Class A tolerance





#### Headquarter

SARBAK METAL TİC. ve SAN. A.Ş.  
Eğitim Mah. Adım Sok. Oran İş Merkezi No: 10 -18 Kat: 3 Daire No: 39 - 49 34722  
Hasanpaşa / Kadıköy / İstanbul / Türkiye  
T: +90 216 414 45 35 pbx | F: +90 216 414 45 40

#### Factory

Çerkezköy Organize Sanayi Bölgesi Gazi Osman Paşa Mah. 8.Cad. No: 3 59500  
Çerkezköy / Tekirdağ / Türkiye  
T: +90 282 725 19 60 pbx | F: +90 282 725 19 70